

Multi-Cure[®] 921-T Medium-Viscosity Potting Resin for Phenolic and Filled Plastics to Glass and Metal

DESCRIPTION

Dymax Multi-Cure[®] 921-T is a high-tensile-strength, UV-curable resin that is especially well suited when rigid adhesive bonds or potted areas are desired. Multi-Cure[®] 921-T was designed to bond a wide variety of substrates including metal, glass, ceramic, and many thermoset plastics. This resin cures clear and deep. Multi-Cure[®] 921-T can be cured with UV light, and shadowed areas can be cured with heat. Dymax adhesives comply with the Montreal Protocol and U.S. Clean Air Act of 1990. This product is in full compliance with the RoHS Directives 2002/95/EC and 2003/11/EC.

TYPICAL UNCURED PROPERTIES (not specifications)

Solvent Content	None - 100% Reactive Solids	
Chemical Class	Urethane Acrylate	
Appearance	Clear/Straw Liquid	
Solubility	Alcohols/Chlorinated Solvents/Ketones	
Viscosity (20 rpm)	3,500 cP (nominal)	ASTM D-1084

TYPICAL CURED PROPERTIES (not specifications)

Durometer Hardness	D75	ASTM D-2240
Tensile at Break	5,200 psi (35.9 MPa)	ASTM D-638
Elongation at Break	35%	ASTM D-638
Modulus of Elasticity	320,000 psi	ASTM D-638
Tensile Lap Shear (steel-to-steel)	3,600 psi	ASTM D-1002
Tensile Compression Shear		
Glass-to-Glass	4,000 psi (exceeds strength of glass)	DSTM D-250*
Glass-to-Steel	5,000 psi (exceeds strength of glass)	DSTM D-251*
Water Absorption (24 h)	1.1%	ASTM D-570
Boiling Water Absorption (2 h)	3.0%	ASTM D-570
Linear Shrinkage	3%	DSTM D-101*
Coefficient of Linear Thermal Expansion	90×10^{-6} in/in/°C	ASTM D-696
Thermal Limits (brittle/degrades)	-43° to 177°C (-45°/+350°F)	DSTM D-200*

*DSTM refers to Dymax Standard Test Method

ELECTRICAL

Dielectric Strength	1,600 V/mil	ASTM D-1304
Volume Resistivity	$7.5 \times 10^{13} \Omega \cdot \text{cm}$	ASTM D-1304
Surface Resistivity	$2.2 \times 10^{14} \Omega$	ASTM D-1304
Dissipation Factor, 1 MHz	0.06	ASTM D-1304
Dielectric Constant, 1 MHz	4.10	ASTM D-1304



© 2002-2012 Dymax Corporation. All rights reserved. All trademarks in this guide, except where noted, are the property of, or used under license by Dymax Corporation, U.S.A.

Technical data provided is of a general nature and is based on laboratory test conditions. Dymax does not warrant the data contained in this bulletin. Any warranty applicable to the product, its application and use is strictly limited to that contained in Dymax standard Conditions of Sale. Dymax does not assume responsibility for test or performance results obtained by users. It is the user's responsibility to determine the suitability for the product application and purposes and the suitability for use in the user's intended manufacturing apparatus and methods. The user should adopt such precautions and use guidelines as may be reasonably advisable or necessary for the protection of property and persons. Nothing in this communication shall act as a representation that the product use or application will not infringe on a patent owned by someone other than Dymax or act as a grant of license under any Dymax Corporation Patent. Dymax recommends that each user adequately test its proposed use and application before actual repetitive use, using the data in this communication as a general guideline.

Technical Data Collection Prior to 2002

Rev. 06/27/2012

CURE DATA (Using 365 nanometer UV light):

	<u>Cure Time (Seconds)</u>	<u>Intensity (mW/cm²)</u>	<u>Dymax Lamps</u>
Tack-Free Cure (1/8-inch bead)	35	175	5000-EC
Depth of Cure (1/4 inch)	30	175	5000-EC
Fixture Between Glass Slides	1-2	50	2000-EC

Shadowed areas can be cured with activator or heat.

Activator is placed on one surface and the adhesive on the mating surface. Curing takes place at room temperature when the parts are mated. Activator requires well-mated parts (up to 0.010-inch gap). Well-mated parts fixture (achieve handling strength) in less than a minute. See Dymax Technical Bulletin "Guidelines for Activator Curing" for complete instructions for all activators.

Heat may be used after UV cure to cure shadowed areas or, after activator cure, to accelerate cure. The following guidelines depend on the amount of adhesive:

<u>Minimum Adhesive Temperature</u>	<u>Time</u>
110°C (225°F)	60 Minutes
120°C (250°F)	30 Minutes
150°C (300°F)	15 Minutes

DISPENSING AND HANDLING ADHESIVE

Multi-Cure® 921-T adhesive may be dispensed with a variety of automatic bench-top syringe applicators or other equipment as required. Questions relating to dispensing and curing systems for specific applications should be referred to Dymax Application Engineering.

Wear impervious gloves and/or barrier cream. Repeated or continuous skin contact with liquid adhesive will cause irritation and should be avoided. Do not wear absorbent gloves. Remove adhesive from skin with soap and water. Never use solvents to remove adhesive from skin or eyes.

STORAGE AND SHELF LIFE

Store material in a cool, dark place when not in use. Do not expose to UV light or sunlight. Material may polymerize upon prolonged exposure to ambient light. Replace lid immediately after use. This material has a minimum 12-month shelf life from date of shipment, unless otherwise specified, when stored between 10°C [50°F] and 32°C [90°F] in the original, unopened container.

CAUTION

For industrial use only. Avoid breathing vapors. Avoid contact with eyes and clothing. In case of contact, immediately flush with water for at least 15 minutes and get medical attention. Wash clothing before reuse. Keep out of reach of children. Do not take internally. If swallowed, induce vomiting at once and call a physician. Repeated or continuous skin contact with liquid adhesive will cause irritation and should be avoided. For specific information, refer to the product Material Safety Data Sheet.